

Maintenance-free plain bearing material E40-B

E40-B is the new sliding material of Schaeffler Group Industrial for maintenance-free metal/polymer composite plain bearings. The basis of the dry lubricant is polytetrafluorethylene (PTFE) with embedded chemically non-reactive additives.

Structure The three-layered material consists of a bronze backing, a sliding layer and a running-in layer, *Figure 1*.




Figure 1
Maintenance-free plain bearing material E40-B

The bronze backing has a sintered porous tin/bronze sliding layer whose pores are filled with the dry lubricant of the running-in layer.

Bronze backing

Chemical element	Maximum proportion of mass w_{\max} %	Hardness HB
Tin Sn	8,5	≈ 100
Phosphorus P	0,4	
Copper Cu	Balance	

Sliding and running-in layer

Chemical element	Proportion of mass w %		Layer thickness mm	
	Sliding layer	Running-in layer	Sliding layer	Running-in layer
Molybdenum disulphide MoS_2	–	max. 8	0,2 – 0,4	0,01 – 0,05
Polytetrafluorethylene PTFE	–	80 – 86		
Fillers	max. 5,5	max. 19		
Tin Sn	7 – 12	–		
Copper Cu	Balance	–		

Application

The lead-free material conforms to the regulations for lead-free plain bearings. It is maintenance-free throughout its life and can be used in the temperature range from -200 °C to $+280\text{ °C}$.

**Schaeffler Technologies
GmbH & Co. KG**

Industriestraße 1–3
91074 Herzogenaurach (Germany)
Internet www.ina.com
E-Mail info@schaeffler.com

In Germany:

Phone 0180 5003872
Fax 0180 5003873

From other countries:

Phone +49 9132 82-0
Fax +49 9132 82-4950

**Schaeffler Technologies
GmbH & Co. KG**

Georg-Schäfer-Straße 30
97421 Schweinfurt (Germany)
Internet www.fag.com
E-Mail FAGinfo@schaeffler.com

In Germany:

Phone 0180 5003872
Fax 0180 5003873

From other countries:

Phone +49 9721 91-0
Fax +49 9721 91-3435

Every care has been taken to ensure the correctness of the information contained in this publication but no liability can be accepted for any errors or omissions. We reserve the right to make technical changes.

© Schaeffler Technologies GmbH & Co. KG
Issued: 2011, January

This publication or parts thereof may not be reproduced without our permission.
PDB 14 GB-D